



Construct Porcelánico

HIGH PERFORMANCE CEMENT-BASED
TILE ADHESIVE C1TE

Highly moisture-resistant adhesive, for laying ceramic tiles of medium / high / low porosity, both indoors and outdoors. High adhesive strength. Particularly recommended for ceramic tiling in swimming pools.

- High slip resistance
- For laying porcelain ceramics
- High setting time

DESCRIPTION

Cement-based tile adhesive, classified as C1TE in accordance with Standard UNE-EN 12004. The adhesive develops strong bond strength and excellent slip resistance guaranteed by the quality of its chemical bonding materials and additives. The technology used in **Construct Porcelánico** adhesive gives the product an appropriate rheology as well as a reduced slip, as a result of the copolymers incorporated in the mixture.

APPLICATION SURFACES

Conventional surfaces and cement-based mortar floors and walls. The application surface must be hard, perfectly set and free from dust, paint, oil, etc.

INSTRUCTIONS FOR USE



- 1 Add water and mix by hand or mechanically until you obtain a smooth paste of a workable consistency.
- 2 Leave the paste to stand for 5 minutes and mix again before applying.
- 3 Spread the paste on the surface in sections of a surface area no larger than 2 m², combing with a suitable trowel. If double gluing is required, spread the mixture over the back of the tile as well.
- 4 Put ceramic tiles on top of the freshly laid adhesive, pressing lightly to ensure that the whole tile surface comes into contact with the adhesive, filling any grooves.
- 5 Leave a joint of a width of at least 1,5 mm between indoor tiles and at least 5 mm between outdoor tiles. Wait 24 hours before grouting wall tiles and 48 hours before grouting floor tiles.
- 6 Respect all perimeter and structural joints. Place one partition joint every 50 m² for indoor floor tiling, and one every 30 m² for outdoor floor tiling.

APPLICATIONS

Tiling indoor floors and walls and outdoor floors using ceramic tiles of medium / high / low porosity. Suitable for laying all types of ceramic tiles.

Suitable for laying marble, "gresite" vitreous paste and porcelain tiles. A double glue technique should be used for tiles larger than 900 cm² (30 cm x 30 cm).

WARNINGS AND RECOMMENDATIONS

- For gypsum surfaces, use **aplicaCer Especial Yeso** and **aplicaCer Capa Gruesa Extra** for low absorption tiles. Avoid applying on dead gypsum or weak renderings.
- Do not apply this product when frost or rain are forecasted.
- Do not apply at temperatures below 5 °C or above 35 °C.
- In extreme weather conditions (wind or high temperatures), the product will dry more quickly than usual. This will result in a shorter open time.
- In high temperatures, windy conditions or if the application surface is very absorbent, it is advisable to moisten the surface and wait for the film of water to disappear before applying the product.
- Check periodically that a surface film has not formed on the adhesive paste once it has been spread onto the surface. If a film is formed, remove the product and apply a fresh coat.
- Check that the paste is sticky enough by periodically lifting one of the tiles already in place to ensure that it is well stuck down.
- Use within a year of date of packaging. Store the product in its original packaging in a dry, covered place protected from humidity.

Construct Porcelánico

HIGH PERFORMANCE CEMENT-BASED
TILE ADHESIVE C1TE



CEMENT-BASED
ADHESIVES

PACKAGING

Construct Porcelánico is available in 25 kg paper bags with moisture-proof plastic lining, dispatched on shrink-wrapped pallets weighing a total of 1,600 kg (64 bags).

TECHNICAL FEATURES

Appearance	White dust	Adhesive strength under normal conditions	$\geq 0,5 \text{ N/mm}^2$
Grain size	$< 1 \text{ mm}$	Adhesive strength after water cycle	$\geq 0,5 \text{ N/mm}^2$
Powder density	1,4 Kg/l	Adhesive strength after heat cycle	$\geq 0,5 \text{ N/mm}^2$
Mixing water	5,5-6 l/bag	Adhesive strength after freeze/thaw cycles	$\geq 0,5 \text{ N/mm}^2$
Pot life	3 hours	Yield:	
Paste density	1,6 kg/l	- single glue	3 - 4 kg/m ²
Open time	30 minutes	- double glue	6 - 8 kg/m ²
Adjustment time	25 minutes		
Slip	$\leq 0,5 \text{ mm}$		

Data based on tests carried out under normal laboratory conditions $23 \pm 2^\circ\text{C}$ and $50 \pm 5\% \text{HR}$ $< 0.2 \text{ m/s}$

NOTE

The recommendations for use are based on our own knowledge and experience. The technical data provided have been obtained under normal laboratory conditions, and may therefore vary according to the environmental conditions in the place where the product is used. As the application conditions are beyond our control, the information provided here does not imply that the company accepts responsibility for any variations.